

SPARPHOS 90 NS MORTAR

Recommended Service Temperature Limit, °C, (°F)	1760 (3200)
Bond TypeChemical
Minimum time before firing, hours	00 hrs.
Storage Life/conditions (months)	3 (cool,dry)
Packaging, weight per container, Kg (lb)	22.7 (50)

Typical Chemical Analysis, % (Calcined Basis)

Al ₂ O ₃	91.9	Fe ₂ O ₃	0.1	Na ₂ O	0.2
SiO ₂	1.2	P ₂ O ₅	6.59		

Note: Data are averaged results of laboratory tests conducted under applicable and current ASTM standards, except where noted. Data should not be used for exact specification purposes.