

SPARSET 85P

SPARSET 85P is an 85% alumina phosphate bonded mortar, with a maximum service temperature of 3100°F.

TYPICAL CHEMICAL ANALYSIS, %

Al ₂ O ₃	82.6
SiO ₂	7.7
Fe ₂ O ₃	0.3
TiO ₂	0.3
MgO	0.1
CaO	0.1
P ₂ O ₅	8.6
Alkalies	0.3

SPARSET 93S is available in 50[#] pails, palletized and shrink-wrapped.

NOTE: DRY MORTAR MUST BE STORED IN DRY PLACE

Data shown are average results of standard ASTM tests unless otherwise noted. Results may vary subject to variations in manufacturing, testing, and installation procedures in the field.