

**SPARPLAS 70P**

**SPARPLAS 70 P** is a 70% alumina phosphate bonded refractory with a maximum service temperature of 3100° F.

**TYPICAL CHEMICAL ANALYSIS, %**

Al <sub>2</sub> O <sub>3</sub>	69.80
SiO <sub>2</sub>	20.40
P <sub>2</sub> O <sub>5</sub>	5.25
TiO <sub>2</sub>	2.69
Fe <sub>2</sub> O <sub>3</sub>	1.36
CaO	0.20
MgO	0.12
Alkalies	0.18

**SPARPLAS 70 P** is available in 1 7/8" or 2 3/4" slices, packaged in 75# poly lined corrugated boxes, 3600# per pallet.

**NOTE: MATERIAL MUST BE STORED IN COOL PLACE**

Data shown are average results of standard ASTM tests unless otherwise noted. Results may vary subject to variations in manufacturing, testing, and installation procedures in the field.