

SPARCON 28P Fine

SPARCON 28P Fine is a high strength, low-cement bonded refractory designed for installation by vibration casting. **SPARCON 28P Fine** is designed for use in precast applications where superior surface finish and high strength are needed.

PHYSICAL PROPERTIES

| | |
|---|--|
| Maximum Service Temperature | 2800°F |
| Dry Castable Requirement | 133 - 143 lbs./cu.ft. |
| Typical water requirement: | <u>vibratable consistency</u> 8.00 – 8.50% |
| Erosion Resistance (ASTM C704) | Less than 14 cc loss. (Typical: 9 – 12 cc loss) |
| Modulus of Rupture After Heating to 1500°F | 1000-2000 lbs/sq.in. |
| Cold Crushing Strength After Heating to 1500°F | 8500-13000 lbs/sq.in. |
| Linear Change, % After Heating to 1500°F | 0.0 to -0.6 |
| Typical Chemical Analysis, % | |
| Al ₂ O ₃ | 47.7 |
| SiO ₂ | 48.0 |
| CaO | 1.5 |
| TiO ₂ | 1.6 |
| Fe ₂ O ₃ | 0.9 |
| MgO | 0.1 |
| Alkalies | 0.2 |

SPARCON 28P Fine is available in 55[#] bags and bulk bags, palletized and shrink-wrapped.

NOTE: CASTABLES MUST BE STORED IN A DRY PLACE

Data shown are average results of standard ASTM tests unless otherwise noted. Results may vary subject to variations in manufacturing, testing, and installation procedures in the field.