

## SPARSET 40 H

**SPARSET 40 H** is a 40% alumina air-setting mortar with a maximum service temperature of 3000°F.

### TYPICAL CHEMICAL ANALYSIS, %

|                                |      |
|--------------------------------|------|
| Al <sub>2</sub> O <sub>3</sub> | 42.8 |
| SiO                            | 50.3 |
| Fe <sub>2</sub> O <sub>3</sub> | 1.8  |
| TiO <sub>2</sub>               | 1.7  |
| MgO                            | 0.3  |
| CaO                            | 0.2  |
| Alkalies                       | 2.9  |

**SPARSET 40 H** is available in 60# pails, 36 pails per pallet and shrink-wrapped.

**NOTE: MATERIAL MUST BE STORED IN COOL PLACE**

Data shown are average results of standard ASTM tests unless otherwise noted. Results may vary subject to variations in manufacturing, testing, and installation procedures in the field.