

SPARSET 70 DM

SPARSET 70 DM is a dry 70% alumina air-setting mortar mix with a maximum service temperature of 3100°F.

TYPICAL CHEMICAL ANALYSIS, %

Al ₂ O ₃	69.2
SiO	23.7
Fe ₂ O ₃	1.5
TiO ₂	2.4
MgO	0.1
CaO	0.1
Alkalies	3.0

SPARSET 70 DM is available in 50# bags, 60 bags per pallet and shrink-wrapped.

NOTE: MATERIAL MUST BE STORED IN COOL PLACE

Data shown are average results of standard ASTM tests unless otherwise noted. Results may vary subject to variations in manufacturing, testing, and installation procedures in the field.