

## **SPARSET 90P**

**SPARSET 90P** is a high alumina, phosphate bonded mortar with a maximum service temperature of 3100°F.

Approximate amount required for 1000  
9" equivalents 450 – 500 lbs

Modulus of Rupture at Joints  
After drying at 230°F 400 – 800 psi

### **TYPICAL CHEMICAL ANALYSIS, %**

Al <sub>2</sub> O <sub>3</sub>	87.8
SiO <sub>2</sub>	5.0
Fe <sub>2</sub> O <sub>3</sub>	0.2
TiO <sub>2</sub>	0.1
MgO	0.1
CaO	0.1
P <sub>2</sub> O <sub>5</sub>	6.4
Alkalies	0.2

**SPARSET 90P** is available in 60<sup>#</sup> pails, palletized and shrink-wrapped.

### **NOTE: DRY MORTAR MUST BE STORED IN DRY PLACE**

Data shown are average results of standard ASTM tests unless otherwise noted. Results may vary subject to variations in manufacturing, testing, and installation procedures in the field.